

Product/Chemical #: Fiberglass Reinforced Polymer (FRP) PT Cross Arm

Date of Preparation: 3/28/2016



CREATIVE PULTRUSIONS, INC.

214 Industrial Lane, Alum Bank, PA 15521
814.839.4186 · Fax: 814.839.4276 · Toll free 888.CPI.PULL
Email: crpul@pultrude.com · www.creativepultrusions.com

Safety Data Sheet

Product/Chemical #: Fiberglass Reinforced Polymer (FRP) PT Cross Arm

Date of Preparation: 3/28/2016

Section 1 – Materials and Company Identification

Product/Chemical Name: Thermoset Polyester Fiberglass Reinforced Composite

Trade Name: Powertrusion Products

General Use: Structural Component

Manufacturer: Creative Pultrusions, Inc., 214 Industrial Lane, Alum Bank, PA 15521-8304

PHONE (814) 839-4186, FAX (814) 839-4276 (8:00AM – 4:30PM EST)

24 Hour Emergency Phone Number: (814) 839-4186

Section 2 – Hazards Identification

GHS-US Classification: As manufactured this product is considered non-hazardous according to GHS.

Label Elements: None required

Other Hazard(s): Product will form dust and particulate matter when drilling, grinding, cutting or sanding. Dust is combustible.

Acute Effects

Inhalation: Fibrous glass dust from machining can cause irritation.

Eye: Fibrous glass dust from machining can cause irritation.

Skin: Fibrous glass dust from machining can cause irritation.

Ingestion: N/A

Carcinogenicity: N/A

Medical Conditions Aggravated by Long-Term Exposure: N/A

Section 3 – Material Composition and Information on Ingredients

<u>Ingredient Name</u>	<u>CAS Number</u>	<u>Percent by Weight</u>
Polymerized Polyester Resin Mixture	None	25%-55%
Fiberglass	659997-17-3	45%-75%

Section 4 – First Aid Measures

Inhalation: Remove from dust to fresh air.

Eye Contact: Flush with water or eye rinse.

Skin Contact: Wash with soap and cold water.

Ingestion: N/A

If condition persists, get appropriate in-plant medical support or consult physician.

Product/Chemical #: Fiberglass Reinforced Polymer (FRP) PT Cross Arm

Date of Preparation: 3/28/2016

Section 5 – Fire Fighting Measures

Flash Point: 675°F / 357.2°C (dust)

Extinguishing Media: Water, Foam, Type A, B, or C extinguishers

Unusual Fire or Explosion Hazards: Do not expose fine dust to an ignition source.

Hazardous Combustion Products: Heavy Smoke, CO, CO₂, and irritating or toxic vapors and gases

Fire-Fighting Instructions: Use self-contained breathing apparatus

Section 6 – Accidental Release Measures

The product as manufactured is non-hazardous. In areas where drilling, grinding, cutting or sanding occurs on this product, care should be taken to clean up dust. Dust deposits should not be allowed to accumulate on surfaces. Dust is considered a St 1 class dust with a Kst (bar-m/s) of less than 100. Avoid dispersal of dust with compressed air.

Section 7 – Handling and Storage

Minimize dust generation and accumulation through routine housekeeping to ensure that dusts do not accumulate on surfaces.

Protective gloves are recommended for handling material comfortably. Long sleeved shirts and pants minimize exposure to nuisance dust.

Section 8 – Exposure Controls/Personal Protection

Component	CAS	Percent	ACGIH TLV	OSHA PEL	Units
Polymerized Polyester Resin Mixture	None	25%-55%	Not Established	Not Established	Not Established
Fiberglass	659997-17-3	45%-75%	Not Established	Not Established	Not Established
Fibrous Glass Dust	None	N/A	5	15 (total)	mg/m ³

Engineering Controls / Ventilation: Must comply with NFPA 68

Respiratory Protection: None required if dust is not present. When dust exposures have the potential to exceed regulated values, a NIOSH approved dust mask must be used.

Eye Protection: Safety glasses with side shields or goggles.

General: Safety Glasses, Gloves, long sleeved shirts and pants recommended.

Section 9 – Physical and Chemical Characteristics

Appearance: Various colors and shapes structural profiles

Odor: No significant odor

pH: N/A

Melting Point/Freezing Point: N/D

Initial Boiling Point: N/A

Flash Point: N/A

Evaporation Rate: N/A

Flammability: N/D

Upper/Lower Explosion Limit: N/A

Vapor Pressure: N/A

Vapor Density: N/A

Specific Gravity: 1.61-2.0

Solubility: N/A

Partition Coefficient: N/A

Auto-Ignition Temperature: N/D

Decomposition Temperature: N/D

Viscosity: N/A

Product/Chemical #: Fiberglass Reinforced Polymer (FRP) PT Cross Arm

Date of Preparation: 3/28/2016

Section 10 – Stability/Reactivity

Stability: Product is stable.

Polymerization: Hazardous polymerization will not occur.

Conditions to avoid: Extreme heat, sources of ignition and flames.

Incompatibilities: Do not store with strong oxidizing agents.

Hazardous decomposition products: Heavy Smoke, CO, CO₂, and irritating or toxic vapors and gases.

Section 11 – Toxicological Information

No toxicological test data is available for this product.

Section 12 – Ecological Information

No ecotoxicity test data is available for this product. This product is not expected to present a hazard to aquatic and terrestrial environments.

Section 13 – Disposal Considerations

As supplied this product is non-hazardous. Consult federal, state and local regulations for proper disposal.

Section 14 – Transport Information

DOT Transportation Data (49 CFR 172.101):

Shipping Name: Not Regulated

Shipping Symbols: N/A

Hazard Class: Not Hazardous

ID No.: N/A

Packing Group: Not Determined

Label: Not Required

Special Provisions (172.102): None

Section 15 – Regulatory Information


TSCA Inventory: All ingredients are on the TSCA inventory.

SARA Section 313: None above de minimus quantity.

SARA 311/312: None as supplied.

OSHA Hazardous Communication Categories: Dust is combustible and an irritant.

Canada-WHMIS Classification: Non-hazardous

California Proposition 65:  **WARNING:** This product can expose you to chemicals including styrene, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov.

Section 16 – Other Information

Refer to NFPA 654, standard for the prevention of fire and dust explosion from the manufacturing, processing and handling of combustible particulate solids, for safe handling of dusts generated during processing.

N/D - Not Determined

N/A - Not Applicable

Prepared By: Ronald W. Allison

Last Revision: 01.25.21

Product/Chemical #: Fiberglass Reinforced Polymer (FRP) PT Cross Arm

Date of Preparation: 3/28/2016

Disclaimer: While the information and recommendations set forth in the SDS are believed to be accurate as of the date of the SDS preparation, Creative Pultrusions, Inc. makes no representation or warranty, direct or indirect, regarding their accuracy or completeness nor do we assume any obligations to advise you of any modifications or corrections to or of such information and recommendations of which we may become aware from the date hereof. Recipients are advised to confirm as they may deem acceptable that the information and recommendations are current and applicable to meet their requirements. Since the conditions are methods of use of this product are beyond our control, Creative Pultrusions, Inc. disclaims any and all liability arising out of the use of this product or the information provided herewith.