

Geogrid/nonwoven composite



NAUE GmbH & Co. KG
 Gewerbestr. 2
 32339 Espelkamp-Fiestel
 Germany

Phone: +49 5743 41-0 Fax: +49 5743 41-240
 E-Mail: info@naue.com Internet: www.naue.com

Combigrid® 40/40 Q1 151 GRK 3

Product description:

Composite of a laid geogrid made of stretched, monolithic polypropylene (PP) flat bars with welded junctions and a mechanical bonded filter geotextile welded within the geogrid structure, used for the reinforcement in many fields of civil engineering including road construction, landfill and hydraulic engineering

Property	Test method*	Unit	40/40 Q1 151 GRK 3
Geogrid			40/40 Q1
Raw material	-	-	polypropylene (PP), white
Mass per unit area	EN ISO 9864	g/m ²	240
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	≥ 40 / ≥ 40
Elongation at nominal strength, md / cmd**	EN ISO 10319	%	≤ 8 / ≤ 8
Tensile strength at 1% elongation, md / cmd**	EN ISO 10319	kN/m	8 / 8
Tensile strength at 2% elongation, md / cmd**	EN ISO 10319	kN/m	16 / 16
Tensile strength at 5% elongation, md / cmd**	EN ISO 10319	kN/m	32 / 32
Aperture size, md x cmd**	-	mm x mm	approx. 31 x 31
Production specific elongation	-	%	0
Geotextile			151 GRK 3
Raw material	-	-	polypropylene (PP), white
Mass per unit area	EN ISO 9864	g/m ²	≥ 150
Max. tensile strength, md / cmd**	EN ISO 10319	kN/m	7.5 / 11.0
Elongation at max. tensile strength, md / cmd**	EN ISO 10319	%	40 / 30
Puncture force	EN ISO 12236	N	1,670
Displacement at static puncture strength	EN ISO 12236	mm	30
Detector tested	-	-	yes
Roll dimensions, width x length	-	m x m	4.75 x 100

*based on, **md = machine direction, cmd = cross machine direction

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.