

# Technical Data Sheet



0799-CPR-20

## CARBOFOL® HDPE 406 1,5 F/s GM13

NAUE GmbH & Co. KG  
 Gewerbestrasse 2  
 32339 Espelkamp-Fiestel  
 Germany  
 Phone: +49 5743 41-0 Fax: +49 5743 41-240  
 E-Mail: info@naue.com Internet: www.naue.com

**CARBOFOL®** is a resistant and multifunctional geomembrane (GBR-P) with a structured surface on one side. This geomembrane is used in many fields of sealing applications

Values tested in the structured area if not otherwise indicated

Property	Test Method	Unit	Values**	Testing Frequencies (minimum)
Thickness - average per roll width (tolerance: -5%) - lowest individual of 10 values (tolerance: -10%)	ASTM D5994	mm	1.50	per roll
Asperity height	ASTM D7466	mm	≥ 0.8	every 2 <sup>nd</sup> roll
Density	ASTM D792 / ASTM D1505	g/cm <sup>3</sup>	≥ 0.940	90,000 kg
Melt Flow Rate (MFR), 190°C / 5.0 kg	ASTM D1238 / EN ISO 1133	g/10 min	1 - 3	per production lot
Carbon black content	ASTM D1603	%	2 - 3	9,000 kg
Carbon black dispersion	ASTM D5596	category	1 - 2	20,000 kg
NCTL – Test* Stress crack resistance	ASTM D5397	hours	≥ 500	GRI GM-10
Tensile strength at yield	ASTM D6693	kN/m	≥ 22	9,000 kg
Elongation at yield	ASTM D6693	%	≥ 12	9,000 kg
Tensile strength at break	ASTM D6693	kN/m	≥ 16	9,000 kg
Elongation at break	ASTM D6693	%	≥ 400	9,000 kg
Tear resistance	ASTM D1004	N	≥ 187	20,000 kg
Puncture resistance	ASTM D4833	N	≥ 400	20,000 kg
<b>Oxidative Induction Time (OIT)***</b> a) Standard OIT b) High pressure OIT	ASTM D3895 ASTM D5885	min min	≥ 100 ≥ 400	90,000 kg
<b>Oven Aging at 85°C***</b> (retained after 90 days) a) Standard OIT b) High pressure OIT	ASTM D3895 ASTM D5885	min min	≥ 55 ≥ 320	per each formulation
<b>UV Resistance</b> a) High pressure OIT	ASTM D5885	min	≥ 200	per each formulation

\*values tested in the smooth area of the welding zones; \*\*average result of specified test specimen over the width, unless otherwise indicated; \*\*\*GM13: The manufacturer has the option to select either one of the OIT test methods

Item no.	6008731		
Roll size	length x width	m x m	160 x 5.10
Roll weight	approx.	kg	1,236

The listed technical values are guiding values achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.