

# Geotextile for road construction



NAUE GmbH & Co. KG  
 Gewerbestr. 2  
 32339 Espelkamp-Fiestel  
 Germany

Phone: +49 5743 41-0 Fax: +49 5743 41-240  
 E-Mail: info@naue.com Internet: www.naue.com

## Secutex® R 261 C NGS 4

### Nordic and Baltic Countries

**Product description:**

Needle punched and calendered nonwoven geotextile for application in road construction according to NorGeoSpec 2012

Property	Test method*	Unit	R 261 C NGS 4
Raw material	-	-	polypropylene (PP), white
Mass per unit area	EN ISO 9864	g/m <sup>2</sup>	∅ 265 (239 - 291)
Thickness	EN ISO 9863-1	mm	1.2
Tensile strength, md**	EN ISO 10319	kN/m	≥ 18.5 ∅ 20.5
Tensile strength, cmd**	EN ISO 10319	kN/m	≥ 21.5 ∅ 23.9
Tensile strength, average md / cmd**	EN ISO 10319	kN/m	≥ 20.0
Tensile strain, md**	EN ISO 10319	%	≥ 36 ∅ 45
Tensile strain, cmd**	EN ISO 10319	%	≥ 36 ∅ 45
Tensile strain, average md / cmd**	EN ISO 10319	%	≥ 36
Cone drop diameter	EN ISO 13433	mm	∅ 17 ≤ 21
Energy Index	-	kN/m	≥ 4.5
Water permeability - VI <sub>H50</sub> -Index	EN ISO 11058	m/s	3.0 x 10 <sup>-2</sup>
Opening size	EN ISO 12956	mm	0.06
Static puncture	EN ISO 12236	N	3,400
Product width x length	-	m x m	on request

\*based on, \*\*md = machine direction, cmd = cross machine direction

  
 \_\_\_\_\_  
 Production Management

  
 \_\_\_\_\_  
 Quality Control

The listed technical values are guiding values, achieved in our laboratories and/or independent testing institutes. Our products are subject to changes without prior notice.