



COMPOUND: 798

POLYMER: Polyamide (PA)

DESCRIPTION: Oil Filled Nylon 6, Cast Stock Shapes and Machined parts, Green Colored

Property	Test Method	Typical Values	Units
Specific Gravity	ASTM D792	1.145	-
Water Absorption 24 HRS, Immersion Saturation, Immersion	ASTM D570	0.5 4.5	%
Hardness	ASTM D785	77	SHORE-D
Tensile Strength at Break	ASTM D638	10,000 (68.95)	PSI (MPa)
Elongation at Break	ASTM D638	50	%
Tensile Modulus	ASTM D638	350,000 (2,413.16)	PSI (MPa)
Compressive Strength	ASTM D695	14,250 (98.25)	PSI (MPa)
Compressive Modulus	ASTM D695	350,000 (2,413.16)	PSI (MPa)
Shear Strength	ASTM D732	8,500 (58.60)	PSI (MPa)
Flexural Strength	ASTM D790	15,500 (106.87)	PSI (MPa)
Flexural Modulus	ASTM D790	425,000 (2,830.27)	PSI (MPa)
Izod Impact Strength, Notched	ASTM D256	1.6	FT.LB/INCH
Coefficient of Linear Thermal Expansion	ASTM D696	5.0 (9.0)	X 10 ⁻⁵ °F ⁻¹ (°C ⁻¹)
Heat Deflection Temperature @ 264 PSI (1.82 MPa)	ASTM D648	250 (121.1)	°F (°C)
Maximum Continuous Operating Temperature		230 (110)	°F (°C)
Minimum Operating Temperature		-22 (-30)	

REVISION HISTORY

REV. NONE – Initial Release, 5-14-1990 BJ

REV. A – Updated data sheet format on new template. Added additional test data. 1012-2020 RSK

The descriptions, design and performance information, and recommended uses for the products, tests and data described herein are based generally on our design and manufacturing experience, product testing in specific conditions, and industry standards. The foregoing information is for general guidance only and does not constitute a guaranty or warranty of design or warranty of performance. All warranties regarding the products described herein will be given in writing at the time of sale of such products. Each purchaser of such products must decide if the products are suitable to the intended use of such purchaser.

Arylex®, CDI Energy Products®, OptiSeal® & OptiPak® are registered trademarks of J.H. Fenner & Co. Limited.